


We claim:

1. A thermoplastic molding composition comprising

- A) from 1 to 97.85% by weight of at least one thermoplastic polyester,
- B) from 1 to 97.85% by weight of at least one polycarbonate,
- C) from 1 to 50% by weight of an elastomeric polymer,
- D) from 0.1 to 5% by weight of a phosphorus-containing stabilizer, wherein component D) is composed of an organic phosphonite of the formula (I):



where

m is 0 or 1,

n is 0 or 1,

Y is an oxygen bridge, a sulfur bridge or a 1,4-phenylene bridge, or a bridging unit of the formula $-\text{CH}(\text{R}^2)-$; each of the R-O- and R¹-O-groups, independently of one another, is the radical of an aliphatic, alicyclic or aromatic alcohol which may contain up to three hydroxyl groups, but excluding any arrangement of the hydroxyl groups which permits these to be part of a phosphorus-containing ring (termed monovalent R-O-groups), or two R-O- or, respectively, R¹-O- groups, bonded to a phosphorus atom, in each case independently of one another, together are the radical of an aliphatic, alicyclic or aromatic alcohol having a total of up to three hydroxyl groups (termed bivalent R-O-, or, respectively, R¹-O-groups),

27

R² is hydrogen, C₁-C₈-alkyl or a group of the formula COOR³,
and

R³ is C₁₋₈-alkyl

5

or is composed of at least one inorganic salt of phosphoric
acids,

E) from 0.05 to 2 % by weight of an organic acid, and

10

F) from 0 to 60% by weight of other additives,

where the percentages by weight of components A) to F) give
100%.

15

2. A thermoplastic molding composition as claimed in claim 1,
wherein component A) is composed of a polyalkylene
terephthalate having from 2 to 10 carbon atoms in the alcohol
moiety.

20

3. A thermoplastic molding composition as claimed in claim 1 or
2, wherein component E) is composed of citric acid or of
p-toluenesulfonic acid or of mixtures of these.

25

4. The use of the molding compositions as claimed in any of
claims 1 to 3 for producing moldings, films or fibers.

5. The use of the molding compositions as claimed in any of
claims 1 to 3 for producing exterior bodywork parts.

30

6. A molding of any type, obtainable from the thermoplastic
molding compositions as claimed in any of claims 1 to 3.

35

40

45